## **51245** POLYESTER FILM / POLYESTER NON-WOVEN ELECTRICAL TAPE

# INTERTAPE POLYMER GROUP® TECHNICAL DATA SHEET

### DESCRIPTION

The combination of polyester film and polyester non-woven materials can be used on a wide variety of electrical applications. Multi-purpose tape for applications which require a combination of tear and puncture resistance, high tensile strength with elongation and excellent dielectric strength.

#### **PRODUCT APPLICATIONS**

Ideal for high volume coil wrapping applications, ground and barrier insulation, outer protective wrap for bobbin applications, coil end insulation anchoring leads, and terminal board pads.



100 Paramount Drive, Suite 300 | Sarasota, FL 34232 | USA Customer Service: 800.IPG.8273 | 800.474.8273 Tape Technical Service: 877.447.4832 www.itape.com | info@itape.com

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Our standard term and conditions of sale apply exclusively to all orders, and all liability for damages of any kind, including consequential, exceeding purchase price is excluded. No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications.

EFFECTIVE: 07/24

#### **NOMINAL VALUES**

Backing

The following data are nominal values based on PSTC, ASTM and other standard tests. The data should not be considered as specifications.

Баскіпд
Backing Thickness
Adhesive
Color
Total Thickness
Dielectric Strength
Temp/Class
Insulation Resistance
Tensile Strength
Adhesion to Steel
Elongation
Electrolytic Corrosion
Flammability
Storage Stability
Solvent Resistance
Moisture Resistance
UL File #
*VDE 0340

Polyester Film / Polyester Non-Woven 3.5 mil (0.089 mm) Rubber Thermosetting Natural 5.3 mil (0.134 mm) 5000 Volts 130°C/B 10<sup>5</sup> megohms 31.5 lbs/in (55 N/cm) 85 oz/in (9.3 N/cm) 30% Direct 1.0/A, 1\* BU 2\* Excellent Excellent Excellent E20780

